

AMTOPP TA57

Polypropylene
Inteplast Group

Message:

Antistatic Clear Label
BIAXIALLY ORIENTED POLYPROPYLENE FILM NON HEAT-SEALABLE

General Information			
Features	Antistatic		
Uses	Film		
Physical	Nominal Value	Unit	
Dimensional Stability ¹			
Across Flow, 130°C	< 3.0	%	
Flow, 130°C	< 5.0	%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	57	µm	
Tensile Strength			ASTM D882
MD : Yield	124	MPa	
TD : Yield	248	MPa	
Tensile Elongation			ASTM D882
MD : Break	200	%	
TD : Break	80	%	
Yield ²	19.3	m ² /kg	
Surface Energy			ASTM D2578
-- ³	36	dyne/cm	
-- ⁴	40	dyne/cm	
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	85		ASTM D2457
Haze	3.5	%	ASTM D1003
NOTE			

1.	5 minutes
2.	Internal Method
3.	Corona Side
4.	High Energy Flame Side

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

