

ASI POLYPROPYLENE 3475-01

Polypropylene Impact Copolymer

A. Schulman Inc.

Message:

PP 3475 is a high melt impact copolymer polypropylene used for compounding and injection applications.

General Information			
Features	Good Impact Resistance		
	High Clarity		
Forms	Pellets		
Processing Method	Compounding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	50 to 70	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	26.9	MPa	ASTM D638
Tensile Elongation (Yield)	5.0	%	ASTM D638
Flexural Modulus	1310	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	
Melting Temperature	150	°C	
NOTE			
1.	51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT