

VITAMIDE® AY15BK6685

Polyamide 66

Jackdaw Polymers

Message:

VITAMIDE® AY15BK6685 is a Polyamide 66 (Nylon 66) product filled with 25% glass fabric. It is available in Europe. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fabric,25% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm ³	ASTM D792, ISO 1183
Water Absorption			
24 hr	1.2	%	ASTM D570
23°C, 24 hr	1.2	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	140	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	3.0	%	ASTM D638, ISO 527-2
Flexural Modulus	7300	MPa	ASTM D790, ISO 178
Flexural Strength	210	MPa	ASTM D790, ISO 178
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	255	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	250	°C	ASTM D648, ISO 75-2/A
Melting Temperature	260	°C	ISO 1218, ASTM D2117
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257, IEC 60093
Dielectric Strength	21	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index			
Solution A	450	V	IEC 60112
-- 1	450	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	V-0		UL 94
NOTE			
1.	Solution A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

