

# Elastocon® CLR40

## Thermoplastic Elastomer

## Elastocon TPE Technologies

### Message:

Elastocon® CLR40 is a transparent thermoplastic elastomer that has been developed for applications that require resilience, high strength properties and a good surface finish. Elastocon® CLR40 is FDA compliant and well suited for consumer goods and industrial applications requiring U.V. stability.

Elastocon® CLR40 can be overmolded onto polypropylene.

Elastocon® CLR40 is supplied as ready to use pellets in 1000 lb. quantities.

General Information			
Features	High strength		
	Good UV resistance		
	Excellent appearance		
	Elastic		
Uses	overmolding		
	Industrial application		
	Consumer goods application field		
Agency Ratings	FDA not rated		
Appearance	Clear/transparent		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	43		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1.42	MPa	ASTM D412
Tensile Strength (Yield)	6.50	MPa	ASTM D412
Tensile Elongation (Break)	730	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	166 - 177	°C	
Front Temperature	182 - 188	°C	
Nozzle Temperature	193 - 204	°C	
Mold Temperature	21.1 - 37.8	°C	
Injection Rate	Fast		
Back Pressure	0.689 - 1.38	MPa	
Injection instructions			
Elastocon® CLR40 thermoplastic elastomer compound does not require drying.			
Extrusion	Nominal Value	Unit	
Hopper Temperature	< 79.4	°C	

Cylinder Zone 1 Temp.	149 - 177	°C
Cylinder Zone 2 Temp.	149 - 177	°C
Cylinder Zone 3 Temp.	149 - 177	°C
Cylinder Zone 4 Temp.	149 - 177	°C
Cylinder Zone 5 Temp.	149 - 177	°C
Die Temperature	149 - 177	°C

Extrusion instructions

Compression ratio: 2.5 to 3.0

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT