Petrothene® LM600500

High Density Polyethylene LyondellBasell Industries

Message:

Petrothene LM600500 resin is selected by customers for use in water, milk and juice bottles. LM600500 exhibits excellent rigidity and good processability.

General Information			
Features	Food Contact Acceptable		
	Good Processability		
	Medium Rigidity		
Uses	Bottles		
	Fruit Juice Bottles		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16		40	
kg)	0.35	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	68		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.3	MPa	ASTM D638
Tensile Elongation (Break)	> 600	%	ASTM D638
Flexural Modulus	1520	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Tensile Impact	53.4	J/cm	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	78.0	°C	ASTM D648
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	125	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

