## LITEN RL 58

# Polyethylene Copolymer UNIPETROL RPA

#### Message:

LITEN RL 58 is a linear polyethylene, copolymer with narrow molecular weight distribution, intended for injection moulding. Typical application is manufacture of technical parts and screw caps for packaging of sparkling water and soft drinks. The products exhibit high impact strength and an ESC resistance

LITEN RL 58 meets the hygienic requirements on materials and articles intended for contact with foodstuffs according to Regulation (EC) 1935/2004 of the European Parliament and of the Council, as well as according to Commission Regulation (EU) No 10/2011 including changes and additions.

General Information					
Features	Copolymer				
	Food Contact Acceptable				
	High ESCR (Stress Crack Resist.)				
	High Impact Resistance				
	Narrow Molecular Weight Distribution				
Uses	Caps				
	Engineering Parts				
Agency Ratings	EC 1935/2004				
	EU 10/2011				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.950	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR)			ISO 1133		
190°C/2.16 kg	3.0	g/10 min			
190°C/5.0 kg	11	g/10 min			
Environmental Stress-Cracking Resistance					
(50°C, 100% Detergent, F50)	20.0	hr	ASTM D1693		
Hardness	Nominal Value	Unit	Test Method		
Shore Hardness (Shore D)	57		ISO 868		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress (Yield)	20.0	MPa	ISO 527-2		
Tensile Strain (Yield)	10	%	ISO 527-2		
Flexural Modulus	800	MPa	ISO 178		
Impact	Nominal Value	Unit	Test Method		
Charpy Notched Impact Strength			ISO 179		
-30°C	5.5	kJ/m²			
23°C	15	kJ/m²			

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	124	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

