

Moplen EP301H

Polypropylene Impact Copolymer

LyondellBasell Industries

Message:

LyondellBasell Australia's polypropylene grade EP301H is a low flow impact copolymer with a conventional molecular weight distribution and is formulated with a general-purpose additive package. EP301H is designed for extrusion applications requiring good melt strength and good impact strength at low part weight. End use products typically made from EP301H include extruded sheet, corrugated board and extruded profiles.

General Information			
Additive	Unspecified Additive		
Features	Good Melt Strength		
	Impact Copolymer		
	Low Flow		
	Low Temperature Impact Resistance		
Uses	Corrugated Sheet		
	Profiles		
	Reinforced Panels		
	Sheet		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183/D
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.7	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	68		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	25.0	MPa	ISO 527-2
Flexural Modulus	1150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-20°C	4.0	kJ/m ²	
0°C	6.5	kJ/m ²	
23°C	14	kJ/m ²	
Falling Dart Impact (-40°C)	11.0	J	BS 2782 306B
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	77.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

