

Plexiglas® DRG-100

Polymethyl Methacrylate Acrylic
Altuglas International of Arkema Inc.

Message:

Plexiglas® DRG-100 is an impact modified thermoplastic acrylic resin formulated for injection molding and extrusion applications. This grade is formulated for approved medical applications and has improved gamma resistance compared to DR-100G. It is a heat resistant resin with minimal edge color and provides 10 times the impact resistance of standard acrylics. It is an all-acrylic resin that combines the toughness associated with other impact plastics and the outstanding transparency and UV resistance of conventional acrylic materials. Moldflow simulation data is available.

General Information			
Additive	Impact Modifier		
Features	BPA Free		
	E-beam Sterilizable		
	Ethylene Oxide Sterilizable		
	Good Color Stability		
	Good Dimensional Stability		
	Good Thermal Stability		
	Good Toughness		
	Good UV Resistance		
	Good Weather Resistance		
	High Clarity		
	High Impact Resistance		
	Impact Modified		
	Low Shrinkage		
	Radiation (Gamma) Resistant		
	Scratch Resistant		
Uses	Medical Devices		
	Medical/Healthcare Applications		
Agency Ratings	USP Class VI		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.2	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.80	%	ASTM D955

Water Absorption (24 hr)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	45		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1860	MPa	ASTM D638
Tensile Strength (Yield)	37.9	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	1860	MPa	ASTM D790
Flexural Strength (Yield)	71.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ¹			ASTM D648
0.45 MPa, Annealed	88.9	°C	
1.8 MPa, Annealed	79.4	°C	
Vicat Softening Temperature			
--	97.8	°C	ASTM D1525 ²
--	86.1	°C	ASTM D1525 ³
Thermal Conductivity	0.22	W/m/K	ASTM C177
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index ⁴	1.490		ASTM D542
Transmittance (3180 μm)	90.0	%	ASTM D1003
Haze (3180 μm)	< 2.0	%	ASTM D1003
Additional Information	Nominal Value		Test Method
ASTM Classification	PMMA 0231V1		ASTM D788
NOTE			
1.	Annealing cycle: 4hrs @ 176°F		
2.	Rate A (50°C/h), Loading 1 (10 N)		
3.	Rate A (50°C/h), Loading 2 (50 N)		
4.	ND @ 72°F		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT