

Innothane® IE-70D

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

IE-70D is a 70 shore D polyurethane formulated for room temperature hand-batch processing. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA, or TDI.

General Information			
Features	General Purpose		
Uses	General Purpose		
RoHS Compliance	RoHS Compliant		
Appearance	White		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Hardener	1.06	g/cm ³	
Cured	1.10	g/cm ³	
Base Resin	1.10	g/cm ³	
Molding Shrinkage - Flow	0.50	%	ASTM D2566
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1720	MPa	ASTM D790
Flexural Strength	62.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	60.0	°C	ASTM D648
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 52		
Hardener	Mix Ratio by Weight: 50		
	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Volume: 100		
Demold Time	240 to 360	min	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
25°C ¹	0.045	Pa · s	

25°C ²	0.20	Pa·s	
25°C ³	0.80	Pa·s	
Curing Time (25°C)	1.7E+2	hr	
Gel Time	14 to 20	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	65 to 75		ASTM D2240
Tensile Strength	36.9	MPa	ASTM D638
Tensile Elongation at Break	4.0	%	ASTM D638
NOTE			
1.	Resin		
2.	Mixed		
3.	Hardener		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

