SEETEC LLDPE UF315

Linear Low Density Polyethylene

Lotte Chemical Corporation

Message:

UF315 is manufactured by Unipol process technology.

UF315 has good mechanical properties, excellent optical properties and good processability.

General Information			
Additive	Antiblock		
	Antioxidant		
	Slip		
Features	Antiblocking		
	Antioxidant		
	Good Processability		
	Opticals		
	Slip		
Uses	Film		
RoHS Compliance	RoHS Compliant		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16		<i>40</i>	
kg)	1.1	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	40	μm	
Tensile Strength			ASTM D882
MD : Break, 40 µm,Blown Film	42.2	MPa	
TD : Break, 40 μm,Blown Film	38.2	MPa	
Tensile Elongation			ASTM D882
MD : Break, 40 µm,Blown Film	740	%	
TD : Break, 40 µm,Blown Film	760	%	
Dart Drop Impact (40 µm, Blown Film)	170	g	ASTM D1709
Elmendorf Tear Strength ¹			ASTM D1922
MD : 40.0 µm	58.8	kN/m	
TD : 40.0 μm	107.9	kN/m	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 40.0 µm, Blown Film)	72		ASTM D2457

Blown Film

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

