

MTEGRITY™ LLDPE LL107AA

Linear Low Density Polyethylene

M. Holland Company

Message:

Linear Low Density Polyethylene
Super Hexene
Barefoot
Liners
Industrial Packaging

General Information			
Features	Low density		
	hexene comonomer		
Uses	Packaging		
	Lining		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.916	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	0.75	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD: Break, 25 µm	40.7	MPa	ASTM D882
TD: Break, 25 µm	33.1	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Break, 25 µm	650	%	ASTM D882
TD: Break, 25 µm	950	%	ASTM D882
Dart Drop Impact (25 µm)	550	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm	400	g	ASTM D1922
TD : 25 µm	700	g	ASTM D1922
Additional Information			

* Film properties based on 1 mil film with 3:1 BUR.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

