

Niblend S65 M

Polycarbonate + ABS

Soredi S.p.a.

Message:

PC-ABS alloy of medium thermic resistance for the extrusion of profiles used by the automotive industry

General Information			
Features	Medium Heat Resistance		
Uses	Automotive Applications		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	40.0	MPa	ASTM D638
Tensile Elongation ² (Break)	50	%	ASTM D638
Flexural Modulus ³	1700	MPa	ASTM D790
Flexural Strength ⁴ (Break)	60.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C, 3.20 mm	150	J/m	
23°C, 3.20 mm	350	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	110	°C	ASTM D648
Vicat Softening Temperature	115	°C	ASTM D1525 ⁵
CLTE - Flow (23 to 55°C)	9.0E-6	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Electric Strength (1.00 mm)	25	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	2.90		IEC 60250
Dissipation Factor (1 MHz)	0.050		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

1.60 mm	HB		
3.20 mm	HB		
Glow Wire Ignition Temperature (2.00 mm)	650	°C	IEC 60695-2-13
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		
5.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT