

Clariant PC PC-1100G30TF15

Polycarbonate
Clariant Corporation

Message:

Clariant PC PC-1100G30TF15 is a polycarbonate (PC) material, which contains a 30% glass fiber reinforced material. This product is available in North America and is processed by injection molding.

The main features of Clariant PC PC-1100G30TF15 are:

- flame retardant/rated flame
- high strength
- Good processability
- Hard
- Corrosion resistance

Typical application areas include:

- engineering/industrial accessories
- military applications
- Sporting goods

General Information	
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight
Additive	PTFE lubricant (15%)
Features	Good dimensional stability
	Low friction coefficient
	Rigidity, high
	Rigid, good
	High strength
	Workability, good
	Good corrosion resistance
	Good coloring
	Good chemical resistance
	Good wear resistance
	Good toughness
	Lubrication
	Low or no water absorption
Uses	Gear
	Metal substitution
	Military application
	Sporting goods
	Cam
Appearance	Available colors
	Natural color
Forms	Particle

Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.55	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption			ASTM D570
24 hr	0.060	%	ASTM D570
Saturation	0.16	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	93		ASTM D785
Class r	115		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	121	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	146	°C	ASTM D648
1.8 MPa, not annealed	143	°C	ASTM D648
CLTE - Flow	2.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-1		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	304 - 343	°C	
Middle Temperature	304 - 343	°C	
Front Temperature	304 - 343	°C	
Processing (Melt) Temp	304 - 327	°C	
Melt Temperature (Aim)	316	°C	
Mold Temperature	82.2 - 121	°C	
Injection Rate	Fast		
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	45 - 75	rpm	
Cushion	3.18 - 6.35	mm	

Injection instructions

The minimum injection pressure required to fill the part should be used for the first stage. The hold pressure should be set between 50% and 75% of the injection pressure.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

