

Borlink™ LE0592S

Polyethylene

Borealis AG

Message:

Borlink LE0592S is a crosslinkable black polyethylene compound, specially designed for semiconductive conductor screen and bonded insulation screen of energy cables.

General Information			
Additive	Carbon black		
Features	Crosslinkable		
	Heat resistance, high		
	Thermal stability, good		
Uses	Wire and cable applications		
	Insulating material		
Agency Ratings	AEIC CS9		
	CENELEC HD 632 S1		
	ICEA S-108-720		
	IEC 60840		
	IEC 62067		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Moisture	200	ppm	Karl Fisher
Thermoset ¹			IEC 60811-507
Elongation under load : 200°C	25	%	IEC 60811-507
Permanent deformation : 200°C	0.0	%	IEC 60811-507
Gottfert Elastograph	1.2	N · m	ISO 6502
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	22.0	MPa	ISO 527-2/25
Tensile Strain (Break)	200	%	ISO 527-2/25
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (135°C, 168 hr)	< 20	%	ISO 527
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ISO 3915
23°C	< 1.0E+2	ohms · cm	ISO 3915
90°C	< 1.0E+3	ohms · cm	ISO 3915
Extrusion	Nominal Value	Unit	

Melt Temperature	120 - 135	°C
Extrusion instructions		
Hopper Drying: 60°C		
NOTE		
1.	0.20 MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

