

Topilene® J351F

Polypropylene Impact Copolymer

Hyosung Corporation

Message:

Characteristics:

Low fisheye

High impact strength

Applications:

Retort CPP film

General Information			
Features	High Impact Resistance		
Uses	Film		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.6	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1370	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact			ASTM D256
-10°C	29	J/m	
23°C	98	J/m	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT