

# Flexirene® MT 40 A

Linear Low Density Polyethylene

Versalis S.p.A.

## Message:

Flexirene MT 40 A is a linear low density polyethylene (LLDPE) with antioxidants, suitable for injection moulding application.

Flexirene MT 40 A is characterised by a good processability and impact resistance.

### Main Application

Flexirene MT 40 A is recommended for the production of large sized technical moulding, houseware, closures, lids and bag handles. Flexirene MT 40 A is characterised by an excellent flowability wich makes it ideal for masterbatches preparation for LDPE and LLDPE.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Impact Resistance		
	Good Processability		
	High Flow		
	Low Density		
Uses	Closures		
	Handles		
	Household Goods		
	Lids		
	Masterbatch		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	50	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Injection Molded)	47		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield, Injection Molded	10.0	MPa	
Break, Injection Molded	10.0	MPa	
Tensile Strain (Break, Injection Molded)	> 500	%	ISO 527-2
Flexural Modulus (Injection Molded)	220	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	92.0	°C	ISO 306/A
Melting Temperature	117	°C	Internal Method
Injection	Nominal Value	Unit	
Rear Temperature	160 to 210	°C	
Middle Temperature	160 to 210	°C	
Front Temperature	160 to 210	°C	
Mold Temperature	10.0 to 40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

