Baydur® 263 IMR (600 g/m² Glass Weight)

Polyurethane (MDI)

Covestro - PUR

Message:

Baydur 263 IMR is a black pigmented, two component, low-density, structural RIM (LD-SRIM) system.

Baydur 263 IMR is used in combination with glass reinforcement to mold automotive composite parts. The composite parts are produced by the open pour reaction injection molding process. The liquid resin mixture 's low viscosity and long cream time allows it to fully permeate the glass reinforcement before reacting to form the solid crosslinked polymer. A variety of different fiberglasses can be used for reinforcement, such as: continuous roving glass mat, chopped strand glass mat, or with glass rovings utilizing a chopped glass fiber RIM machine. The system exhibits excellent flow, quick demold times, and outstanding mechanical properties.

Typical composite applications include interior trim consoles, door trim panels, sunshades, and load floors. The Baydur 263 IMR system combines high strength and thermal properties, while still providing lighter weight than ABS, talc filled polypropylene (PP), or blow molded PP. Composites made with Baydur 263 IMR maintain dimensional stability under high heat and humidity conditions, even at thinner cross sections. Baydur 263 IMR can be poured into a mold to produce composite substrates separately, to be finished later with trim cover stock. Or, it can be poured directly behind trim cover stock, such as vinyl, fabric, or carpet, in a one-step process.

The Baydur 263 IMR system is supplied as two reactive liquid components. Component A is a polymeric diphenlymethane diisocyanate (PMDI), and Component B is a formulated polyether polyol system. As with any product, use of the Baydur 263 IMR system in a given application must be tested (including field-testing, etc.) in advance by the user to determine suitability.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 22% filler by weight		
Features	Low viscosity		
	High strength		
	Good liquidity		
Uses	Application in Automobile Field		
	Car interior equipment		
Appearance	Black		
Processing Method	Reaction Injection Molding (RIM)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.549	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (22°C, 3.00 mm)	25.0	MPa	ASTM D638
Flexural Modulus (22°C, 3.00 mm)	1600	MPa	ASTM D790
Flexural Strength (22°C, 3.00 mm)	40.0	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow (3.00 mm)	1.7E-5	cm/cm/°C	ASTM D696
Thermoset	Nominal Value		
Thermoset Components			
Component a	Mixing ratio by weight: 160		
Component B	Mixing ratio by weight: 100		
Additional Information			

Part A Type: Isocyanate Appearance: Dark brown liquid Specific Gravity @ 25°C: 1.24 Viscosity @25°C: 200 cps Flash Point PMCC: 199°C NCO: 31.0 min wt% Part B Type: Polyol Appearance: Black liquid Specific Gravity @ 25°C: 1.05 Viscosity @25°C: 1200 cps Flash Point PMCC: 145°C Hydroxyl Number: 550 KOH/g Material Temperatures: 30 to 40°CMold Temperature: 65 to 75°CCream Time: 20 secGel Time: 45 secTack-Free Time: 55 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

