

Luran® S KR2866C

Acrylonitrile Styrene Acrylate + PC

Styrolution

Message:

Luran S KR2866C is a blend of ASA and PC with a reduced content of PC. It is characterized by a medium impact toughness and heat resistance.

General Information			
Features	Medium Heat Resistance		
	Medium Impact Resistance		
Uses	Automotive Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
220°C/10.0 kg	5.00	cm ³ /10min	
260°C/5.0 kg	11.0	cm ³ /10min	
Molding Shrinkage	0.50 to 0.90	%	ISO 294-4
Water Absorption			ISO 62
Saturation, 23°C	0.90	%	
Equilibrium, 23°C, 50% RH	0.25	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	110	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	60.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.4	%	ISO 527-2
Flexural Stress	90.0	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Tensile Elongation - MD (Break)	15	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	9.0	kJ/m ²	
23°C	35	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	9.0	kJ/m ²	
23°C	55	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, Annealed	113	°C	ISO 75-2/B
1.8 MPa, Annealed	102	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306/B50
CLTE - Flow	8.0E-5 to 1.0E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.17	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	260 to 300	°C	
Mold Temperature	80.0	°C	
Injection Velocity	200	mm/sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

