

# OXPEKK® MG210C

Polyetherketoneketone

Oxford Performance Materials, Inc.

## Message:

OXPEKK® MG210C is a Polyetherketoneketone (PEKK) material filled with 10% carbon fiber. It is available in Europe or North America.

Typical application of OXPEKK® MG210C: Medical/Healthcare

General Information			
Filler / Reinforcement	Carbon Fiber, 10% Filler by Weight		
Uses	Medical/Healthcare Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm <sup>3</sup>	ASTM D792
Water Absorption (24 hr)	< 0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1100	MPa	ASTM D638
Tensile Strength (Break)	193	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	9600	MPa	ASTM D790
Flexural Strength	269	MPa	ASTM D790
Compressive Strength	241	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	163	°C	DSC
Melting Temperature	360	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT