Keliren® CM352J

Chlorinated Polyethylene

Hangzhou Keli Chemical Co., Ltd.

Message:

Chlorine Content

Hardness

Keliren® elastomers called rubber grades of CPE products are formulated into quality extruded, molded, and sheet rubber goods that satisfy critical needs for heat, oil and chemical resistance, compression set, toughness and durability, processibility, and value-related economics. Application: Wire & Cable, etc

Performance: Superior mechanical property and good volume resistance

General Information					
Features	Durable				
	Flame Retardant				
	Good Chemical Resistance				
	Good Processability				
	Good Toughness				
	Good Weather Resistance				
	High Heat Resistance				
	Low Temperature Resistant				
	Oil Resistant				
	Ozone Resistant				
	Soft				
Uses	Appliances				
	Automotive Applications				
	Cable Jacketing				
	Computer Components				
	Conveyors				
	Hose				
	Marine Applications				
	Mining Applications				
	Sheet				
	Wire & Cable Applications				
Processing Method	Extrusion				
	Injection Molding				
	Sheet Extrusion				
Physical	Nominal Value	Unit	Test Method		
Mooney Viscosity (ML 1+4, 121°C)	70 to 80	MU	ISO 289		
			130 203		

wt%

Unit

ISO 7725

Test Method

34.0 to 36.0

Nominal Value

Shore Hardness (Shore A)	< 65		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	> 8.00	MPa	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

