

Chemlon® 207 G

Polyamide 6

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® 207 G is a Polyamide 6 (Nylon 6) material filled with 7.0% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of Chemlon® 207 G are:

- Creep Resistant
- Good Dimensional Stability
- Good Stiffness
- High Strength

General Information			
Filler / Reinforcement	Glass Fiber,7.0% Filler by Weight		
Features	Good Creep Resistance		
	Good Dimensional Stability		
	Good Stiffness		
	High Tensile Strength		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	94.8	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus (23°C)	3410	MPa	ASTM D790
Flexural Strength (23°C)	128	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	182	°C	ASTM D648
Melting Temperature	216	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

