

AKROMID® B3 black (2502)

Polyamide 6
AKRO-PLASTIC GmbH

Message:
AKROMID® B3 black (2502) is a unreinforced polyamide 6.
Applications are holds, housings and cover parts in automotive industry and power tools

General Information				
Uses		Automotive Applications		
		Housings		
		Power/Other Tools		
Appearance		Black		
Resin ID (ISO 1043)		PA6		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.13	--	g/cm ³	ISO 1183
Spiral Flow	107	--	cm	Internal Method
Molding Shrinkage				ISO 294-4
Across Flow	1.0	--	%	
Flow	1.1	--	%	
Water Absorption (Saturation, 23°C)	9.0 to 10	--	%	ISO 62
Humidity Absorption - 62% RH (70°C)	2.6 to 3.4	--	%	ISO 1110
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3600	1200	MPa	ISO 527-2/1
Tensile Stress (Yield)	85.0	45.0	MPa	ISO 527-2/50
Tensile Strain (Break)	20	> 50	%	ISO 527-2/50
Flexural Modulus ¹	3100	--	MPa	ISO 178
Flexural Stress ²	120	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	2.0	--	kJ/m ²	
23°C	5.0	16	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	--		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				

0.45 MPa, Unannealed	180	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	60.0	--	°C	ISO 75-2/A
Melting Temperature ³	220	--	°C	DIN EN 11357-1
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+12	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+10	ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate ⁴ (1.00 mm)	< 100	--	mm/min	FMVSS 302
Flame Rating (1.60 mm)	V-2	--		UL 94
Glow Wire Flammability Index (1.60 mm)	750	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.60 mm)	675	--	°C	IEC 60695-2-13
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	10 K/min, DSC			
4.	> 1 mm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

