Cheng Yu T889G25

Polybutylene Terephthalate

Cheng Yu Plastic Company Limited

Message:

Cheng Yu T889G25 is a polybutene terephthalate (PBT) product, which contains a 25% glass fiber reinforced material. It is available in the Asia-Pacific region. The main characteristics are: flame retardant/rated flame.

| General Information | | | |
|---|---|-------|-------------|
| Filler / Reinforcement | Glass fiber reinforced material, 25% filler by weight | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.36 | g/cm³ | ASTM D792 |
| Molding Shrinkage | | | ASTM D955 |
| Flow | 0.60 - 0.90 | % | ASTM D955 |
| Transverse flow | 1.3 - 1.7 | % | ASTM D955 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (M-Scale) | 94 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Strength | 185 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Unnotched Izod Impact (23°C) | 110 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa, Unannealed) | 227 | °C | ASTM D648 |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | 1.0E+15 | ohms | ASTM D257 |
| Dielectric Constant (60 Hz) | 3.60 | | ASTM D150 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating (1.50 mm) | НВ | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

