

GAPEX® FPP40GQ24WH

Polypropylene
Ferro Corporation

Message:

GAPEX®FPP40GQ24WH is a polypropylene material that contains 40% glass \minerals. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

GAPEX®The main features of the FPP40GQ24WH are:

Impact modification

Chemical coupling

heat stabilizer

General Information			
Filler / Reinforcement	Glass \mineral, 40% filler by weight		
Additive	Impact modifier heat stabilizer		
Features	Impact modification Chemical coupling Thermal Stability		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.5	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.40	%	ASTM D955
Transverse flow	1.1	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	40.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus			ASTM D790
1% secant: 23°C	2830	MPa	ASTM D790
Tangent: 23°C	3230	MPa	ASTM D790
Flexural Strength (23°C)	60.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Unnotched Izod Impact (23°C)	440	J/m	ASTM D4812
Dart Drop Impact (23°C)	1.47	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	152	°C	ASTM D648

1.8 MPa, not annealed	121	°C	ASTM D648
Additional Information			

Testing and measurements were performed at 73 +/-3°F and 50 +/-5% relative humidity unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

