

Grilon® TSG-30

Polyamide 66/6 Copolymer

EMS-GRIVORY

Message:

Grilon® TSG-30 is a Polyamide 66/6 Copolymer (Nylon 66/6) material filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grilon® TSG-30 are:

- Flame Rated
- RoHS Compliant

Typical applications include:

- Appliances
- Automotive
- Consumer Goods
- Electrical/Electronic Applications
- Engineering/Industrial Parts

General Information				
UL YellowCard		E53898-592186		
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Uses		Appliance Components		
		Automotive Applications		
		Consumer Applications		
		Electrical/Electronic Applications		
		Engineering Parts		
		Household Goods		
		Industrial Applications		
		Power/Other Tools		
		Sporting Goods		
RoHS Compliance		RoHS Compliant		
Forms		Granules		
Processing Method		Injection Molding		
Multi-Point Data		Shear Modulus vs. Temperature (ISO 11403-1)		
		Specific Volume vs Temperature (ISO 11403-2)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.34	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.70	--	%	
Flow	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	6.5	--	%	

Equilibrium, 23°C, 50% RH	2.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	210	110	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9700	6000	MPa	ISO 527-2
Tensile Stress (Break)	175	120	MPa	ISO 527-2
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m²	
23°C	13	20	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	65	65	kJ/m²	
23°C	75	85	kJ/m²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	220	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	135	--	°C	ISO 75-2/C
Continuous Use Temperature				Internal Method
-- ¹	100 to 120	--	°C	
-- ²	220	--	°C	
Melting Temperature ³	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.0E-5	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	IEC 60093
Electric Strength	25	24	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA 66+PA 6, MHR, 14-100 N, GF30			ISO 1874
NOTE				
1.	Long Term			
2.	Short Term			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

