

# Tecnoflon® T 636/L

Fluoroelastomer  
Solvay Specialty Polymers

## Message:

TECNOFLON® T 636/L is a low viscosity fluoroelastomer terpolymer designed to provide improved low temperature characteristics. Tecnoflon® T 636/L does not contain curatives: therefore the proper levels of Tecnoflon® FOR M1 and Tecnoflon® FOR M2 must be added to achieve the required properties. Tecnoflon® T 636/L is a lower viscosity version of Tecnoflon® T 636: please refer to Tecnoflon® T 636 Technical data sheet for data on chemical resistance: Tecnoflon® T 636/L exhibits the same excellent heat and chemical resistance expected from Tecnoflon® copolymers.

Some of the basic properties of TECNOFLON® T 636/L are:

- Improved low temperature performance
- Good heat and chemical resistance
- Very low compression set
- Excellent mould release
- Lack of mould fouling
- Superior mould flow

Tecnoflon® T 636/L can be used for compression, injection and transfer molding of O-rings, diaphragms, gaskets, seals, moulded shapes or other items requiring improved low temperature performance. Tecnoflon® T 636/L can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting.

Finished goods can be produced by a variety of rubber processing methods.

General Information	
Features	Good Chemical Resistance
	Good Flow
	Good Mold Release
	High Heat Resistance
	Low Compression Set
	Low Viscosity
	Terpolymer
Uses	Belts/Belt Repair
	Blending
	Diaphragms
	Gaskets
	Hose
	Low Temperature Applications
	Profiles
	Seals
Appearance	Sheet
	Translucent
Forms	Slab
Processing Method	Calendering
	Compounding
	Compression Molding

Extrusion  
Injection Molding  
Resin Transfer Molding

Physical	Nominal Value	Unit
Mooney Viscosity <sup>1</sup> (ML 1+10, 121°C)	22	MU
Fluorine Content <sup>2</sup>	66	%
NOTE		
1.	Raw polymer	
2.	Raw polymer	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

