

Trilliant™ HC HC6200-5002 XR Grey

Polyamide 12
PolyOne Corporation

Message:

The Trilliant® specialty compounds offer a complete system of specialty engineered materials, certified processes, services and technical support that enable healthcare OEM's to get to market ahead of competition. When specified, Trilliant® compound may incorporate agency rated materials that meet USP Class IV, FDA or ISO 10993 testing requirements.

This Trilliant® grade is a high density specialty compound featuring a sustainable material solution for radiation shielding and weighting & balancing applications. The composite material offers a high performance thermoplastic-based alternative to lead. This compound has densities similar to traditional metals and provides greater flexibility in design and processing.

General Information			
Features	High specific gravity		
	Non-toxic		
	Medium impact resistance		
Uses	Weights and balances		
	Radiation shielding		
	Shell		
	Medical/nursing supplies		
Appearance	Grey		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	8.00	g/cm ³	ISO 1183
Molding Shrinkage	1.0 - 1.5	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5000	MPa	ISO 527-2/1
Tensile Stress (Break)	45.0	MPa	ISO 527-2/50
Tensile Strain (Break)	1.0 - 2.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	15	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	150	°C	ISO 75-2/B
1.8 MPa, not annealed	110	°C	ISO 75-2/A
Thermal Conductivity	1.5 - 2.0	W/m/K	ASTM E1461
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+3	ohms	IEC 60093
Additional Information			

Shielding properties:Attenuation coefficient at 511 keV = 0.72cm-1Half Thickness at 511 keV = 0.96cm

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	4.0	hr
Processing (Melt) Temp	230 - 280	°C
Mold Temperature	65.0 - 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

