THERMOLAST® K TP3CDB (Series: EX)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The EX Series is your material solution for extrusion applications such as door seals and window gaskets. The compounds are available in natural and black colors.

Typical applications

Edge guards

Profiles for furniture

Seals for windows and doors

Material advantages

Alternative material to PVC-P

Easy coloring (compounds in natural colors)

Easy to extrude

Excellent mechanical properties

Excellent weldabililty

Halogen-free

No interaction with other materials (e.g. PVC-U, PP, PS, ABS, POM, PA, PC, PMMA)

Recyclable

Resistant to acrylic paints

| General Information | | | |
|---|---------------------|-------|-------------|
| Features | Good Colorability | | |
| | Halogen Free | | |
| | Recyclable Material | | |
| | Weldable | | |
| | | | |
| Uses | Furniture | | |
| | Gaskets | | |
| | Profiles | | |
| | Seals | | |
| | | | |
| Appearance | Natural Color | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.14 | g/cm³ | ISO 1183 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore A) | 26 | | ISO 7619 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress ¹ (Yield) | 3.50 | MPa | ISO 37 |
| Tensile Elongation ² (Break) | 500 | % | ISO 37 |
| Tear Strength ³ | 9.0 | kN/m | ISO 34-1 |
| Compression Set ⁴ | | | ISO 815 |

| -25°C, 24 hr | 70 | % | |
|-----------------------|---------------------------|------|--|
| 23°C, 72 hr | 12 | % | |
| 70°C, 24 hr | 48 | % | |
| 100°C, 24 hr | 83 | % | |
| Extrusion | Nominal Value | Unit | |
| Drying Temperature | 60.0 to 80.0 | °C | |
| Drying Time | 2.0 to 4.0 | hr | |
| Cylinder Zone 1 Temp. | 140 | °C | |
| Cylinder Zone 2 Temp. | 150 | °C | |
| Cylinder Zone 3 Temp. | 160 | °C | |
| Die Temperature | 180 to 190 | °C | |
| NOTE | | | |
| 1. | Type S2, 200 mm/min | | |
| 2. | Type S2, 200 mm/min | | |
| 3. | Method Bb, Angle (Nicked) | | |
| 4. | Method A | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

