

Moplen HP2814

Polypropylene Homopolymer

LyondellBasell Industries

Message:

Moplen HP2814 is used in extrusion applications. It has a very narrow molecular weight distribution and it is formulated with an anti-gasfading stabilisation package. Moplen HP2814 is used in the production of continuous filaments. Typical applications are high-tenacity yarns (HTY) and spunbond nonwovens. For regulatory information please refer to Moplen HP2814 Product Stewardship Bulletin (PSB).

General Information			
Additive	Anti-smoke fade		
Features	Homopolymer		
	Narrow molecular weight distribution		
Uses	Spunbond nonwoven fabric		
	Non-woven fabric		
	Filament		
	Line		
Processing Method	Continuous Filament/Spinning		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	20.0	MPa	ISO 527-2
Fracture	20.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	11	%	ISO 527-2
Fracture	> 500	%	ISO 527-2
Flexural Modulus	1300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	4.0 - 140	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
Vicat Softening Temperature			
--	153	°C	ISO 306/A50
--	93.0	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT