

BLUESTAR® PBT 201-G25202

Polybutylene Terephthalate

Nantong Zhonglan Engineering Plastics Co., Ltd.

Message:

BLUESTAR® PBT 201-G25202 is a Polybutylene Terephthalate (PBT) product filled with 25% glass fiber. It is available in Asia Pacific or North America. Applications of BLUESTAR® PBT 201-G25202 include electrical/electronic applications and lighting applications. Primary characteristic: flame rated.

General Information			
UL YellowCard	E255317-100032018		
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Uses	Electrical/Electronic Applications		
	Lighting Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.58	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.40	%	
Across Flow	0.80	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.17	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ASTM D638
Tensile Strength (Break)	110	MPa	ASTM D638
Flexural Modulus	7500	MPa	ASTM D790
Flexural Strength	170	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	9.00	kJ/m ²	ASTM D256
Unnotched Izod Impact (Area) (23°C)	55.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	216	°C	
1.8 MPa, Unannealed	206	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.3E+16	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

