

Exceed™ 4518PA

Metallocene Polyethylene Resin

ExxonMobil Chemical

Message:

Edge 4518PA resin is a metallocene ethylene-ethane copolymer. The film made of Edge 4518PA resin has excellent tensile properties, impact resistance and puncture resistance. These excellent properties, together with good stretchability, make it a universal resin suitable for single-layer and multi-layer packaging films and cast stretch films.

General Information			
Additive	heat stabilizer		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	101	MPa	ASTM D882
1% secant, TD	124	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	8.35	MPa	ASTM D882
TD: Yield	7.34	MPa	ASTM D882
MD: Fracture	66.9	MPa	ASTM D882
TD: Fracture	48.1	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	500	%	ASTM D882
TD: Fracture	730	%	ASTM D882
Dart Drop Impact	140	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD	150	g	ASTM D1922
TD	460	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	87		ASTM D2457
Haze	2.2	%	ASTM D1003
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

