

Advanced-PP 1100N

Polypropylene Homopolymer
Advanced Petrochemical Company

Message:

Advanced-PP 1100 N is a propylene homopolymer for general injection molding applications.

Application
Closures,Furniture, Housewares, General injection molding.

Regulatory Information:
The grade Advanced-PP 1100N and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011. Specific information is available upon request.

General Information			
Features	Homopolymer		
Uses	Closures		
	Furniture		
	General Purpose		
	Household Goods		
Agency Ratings	EU 10/2011		
	FDA 21 CFR 177.1520		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	78.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1550	MPa	ISO 527-2/1
Tensile Stress (Yield)	35.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	8.0	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	110	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	3.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	85.0	°C	ISO 75-2/B
Vicat Softening Temperature	154	°C	ISO 306/A50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

