

# Matrixx CPP1B10

Polypropylene  
The Matrixx Group, Inc.

Message:

Matrixx CPP1B10 is a polypropylene material, and its filler is 10% calcium carbonate filler. This product is available in North America and is processed by injection molding. The main characteristics of Matrixx CPP1B10 are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Calcium carbonate filler, 10% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.968	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.1 - 1.5	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.3	MPa	ASTM D638
Flexural Modulus - Tangent	1650	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	37	J/m	ASTM D256
Dart Drop Impact	2.26	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	93.3	°C	ASTM D648
RTI	65.6	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	82.2 - 104	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	188 - 232	°C	
Middle Temperature	188 - 232	°C	
Front Temperature	188 - 232	°C	
Processing (Melt) Temp	199 - 232	°C	
Mold Temperature	21.1 - 48.9	°C	
Injection Rate	Moderate		
Back Pressure	0.138 - 2.07	MPa	
Cushion	6.35 - 12.7	mm	
Injection instructions			

Drying not normally requiredInjection Booster Pressure: Maximum without flash, 60% of machine maximum, targetScrew Speed: Slow to Medium

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

