VESTAMID® NRG 4901 black

Polyamide 12

Evonik Industries AG

Message:

For Steel Pipe Protection (Encasement)
VESTAMID® NRG 4901 black offers a flexible, mechanically tough encasement system that combines the advantages of polyethylene coating and cement
mortar casing.
Uses of VESTAMID® NRG Products:
The important advantages of VESTAMID® NRG 4901 as an encasement material are:
unusually high impact resistance and toughness, even at low temperatures
excellent stress cracking resistance
excellent wear resistance
low sliding friction coefficient
Product characteristics compared with other encasement materials:
VESTAMID® NRG 4901 black has higher Shore hardness than polyethylene or polypropylene. In contrast to polyethylene or propylene encasement,
therefore, the polyamide encasement offers, apart from the corrosion protection provided by the barrier effect, also mechanical protection for the
encased steel pipe.
Application areas for the new encasement material are found in non-conventional installation technologies such as:

horizontal directional drilling

the soil displacement method with non-steered displacement hammers

dynamic ramming

plow technology

We recommend a processing temperature between 230°C (446°F) and 260°C (500°F) - in some cases up to 280°C (536°F) - during the extrusion process. Drying at 80°C (176°F) for 2 hours to 4 hours before processing is recommended.

General Information			
Features	Durable		
	Good Toughness		
	High Molecular Weight		
	Hydrocarbon Resistant		
Appearance	Black		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.02	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	73		ISO 868
Ball Indentation Hardness ¹	76.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1350	MPa	ISO 527-2
Tensile Stress (Yield)	40.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	12	%	
Break	> 150	%	
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			
(-40°C)	No Break		ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	170	°C	ISO 306/A
Melting Temperature ²	177	°C	ISO 11357-3
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Melt Temperature	230 to 280	°C	
NOTE			
1.	H30		
2.	2nd Heating		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

