

# Tuffalloy™ 4274

Thermoplastic

Hapco Inc.

## Message:

TUFFALLOY 4270 is a series of Liquid Molding Compounds with thermoplastic properties such as high impact, high heat distortion, and low viscosity. This unique chemistry developed by Hapco to meet today's market demands for prototype and low production parts needs.

THE TUFFALLOY 4270 Series are available in (4) speeds.

The user has the ability to use different speeds of TUFFALLOY 4270, typically using a slower speed initially and increasing to a fast set, 1 minute working life.

### PROCESSING:

TUFFALLOY 4270 Series can be pressure cast, vacuum cast, or open cast.

For best results, TUFFALLOY 4274/75 should be used with Hapco's metering/dispensing equipment, RAPIDFIL, MINI FIL, and RAPIDSHOT.

General Information	
Features	Fast Molding Cycle
	High Heat Resistance
	High Impact Resistance
	Low Viscosity
Uses	Automotive Under the Hood
	Closures
	Prototyping
	Tubing
Appearance	Cream
Forms	Liquid
Processing Method	Casting
	Vacuum Casting

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D4669
Molding Shrinkage - Flow	0.20 to 0.80	%	ASTM D2566
Weight - per cubic inch	19	g	
Gel Time <sup>1</sup> (25°C)	2.0	min	ASTM D2971
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	79 to 89		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2820	MPa	ASTM D638
Tensile Strength	79.3	MPa	ASTM D638
Tensile Elongation (Break)	7.0	%	ASTM D638
Flexural Modulus	2850	MPa	ASTM D790
Flexural Strength	98.6	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	80	J/m	ASTM D256
Unnotched Izod Impact	> 110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	90.0	°C	
1.8 MPa, Unannealed	81.0	°C	
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 100, Mix Ratio by Volume: 100		
Part B	Mix Ratio by Weight: 85, Mix Ratio by Volume: 100		
Thermoset Mix Viscosity <sup>2</sup> (25°C)	250 to 350	cP	ASTM D4878
Demold Time (21°C)	8.0 to 20	min	Internal Method
NOTE			
1.	100 g		
2.	Range: 250 to 350		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

