Hostacom ERC 204N C11354

Polypropylene Copolymer LyondellBasell Industries

Message:

Hostacom ERC 204N is a 10% talc filled PP copolymer, with high stiffness, low filler content, good scratch resistance and low odour. Advanced technologies allowed for a significant reduction of mineral filler which contributed to the reduction of final part weight.

This product is also available in other colors, new colors can be developed depending on customer requirements.

For regulatory compliance information, see Hostacom ERC 204N C11354 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| General Information | | | | | |
|---------------------------------------|-----------------------------------|----------|-------------|--|--|
| Filler / Reinforcement | Talc filler, 10% filler by weight | | | | |
| Features | Low density | | | | |
| | Rigidity, high | | | | |
| | Rigid, good | | | | |
| | Copolymer | | | | |
| | Good UV resistance | | | | |
| | Workability, good | | | | |
| | Good liquidity | | | | |
| | Good color stability | | | | |
| | Good wear resistance | | | | |
| | Scratch resistance | | | | |
| | The smell is low to none | | | | |
| | Excellent appearance | | | | |
| | | | | | |
| Uses | Application in Automobile Field | | | | |
| | Car interior parts | | | | |
| | Car dashboard | | | | |
| | | | | | |
| Appearance | Available colors | | | | |
| Processing Method | Injection molding | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Density (23°C) | 0.970 | g/cm³ | ISO 1183/A | | |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | | | |
| kg) | 20 | g/10 min | ISO 1133 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Flexural Modulus ¹ (23°C) | 1900 | MPa | ISO 178/A | | |
| Impact | Nominal Value | Unit | Test Method | | |
| Charpy Notched Impact Strength | | | ISO 179/1eA | | |
| 0°C | 4.0 | kJ/m² | ISO 179/1eA | | |
| 23°C | 6.0 | kJ/m² | ISO 179/1eA | | |
| Thermal | Nominal Value | Unit | Test Method | | |

| Heat Deflection Temperature | (0.45 MPa, | | |
|-----------------------------|------------|----|------------|
| Unannealed) | 100 | °C | ISO 75-2/B |
| NOTE | | | |
| 1. | 1.0 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

