

Kepamid® 2325GF

Polyamide 66

Korea Engineering Plastics Co., Ltd

Message:

Kepamid® 2325GF is a Polyamide 66 (Nylon 66) material filled with 25% glass fiber. It is available in Asia Pacific, Europe, or North America. Primary attribute of Kepamid® 2325GF: Flame Rated.

Typical applications include:

Automotive

Electrical/Electronic Applications

General Information			
UL YellowCard	E120354-220471		
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	25	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	167	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	8340	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	245	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	260	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

