

Ecomass® 1050TU96

Polyamide 12

Ecomass Technologies

Message:

Ecomass®1050TU96 is a polyamide 12 (nylon 12) material containing a tungsten filler. This product is available in North America and is processed by injection molding.

Ecomass®The main features of 1050TU96 are:

Hard

Good toughness

non-toxic

General Information			
Filler / Reinforcement	Tungsten packing		
Features	Semi Rigid		
	High specific gravity		
	Good toughness		
	Non-toxic		
Uses	Radiation shielding		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	11.0	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6450	MPa	ASTM D638
Tensile Strength	34.5	MPa	ASTM D638
Tensile Elongation (Break)	1.8	%	ASTM D638
Flexural Modulus	4960	MPa	ASTM D790
Flexural Strength	48.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	135	°C	ASTM D648
1.8 MPa, not annealed	121	°C	ASTM D648
Additional Information			
Surface Resistivity, ASTM D257: 0.21 ohms/sq			
Injection	Nominal Value	Unit	
Drying Temperature	73.9	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	204 - 254	°C	

Mold Temperature

57.2 - 82.2

°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

