

Tecotek® PC43 GR10 BK002

Polycarbonate
Eurotec Engineering Plastics

Message:
PC, 10% glass fiber reinforced, black

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PC GF10		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	0.50	%	
Flow	0.50	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 0.10	%	ISO 15512
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4000	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	85.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	9.0	kJ/m ²	
23°C	11	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	135	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index (Solution A)	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Glow Wire Flammability Index (2.00 mm)	850	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 to 4.0	hr	
Hopper Temperature	60.0 to 80.0	°C	
Processing (Melt) Temp	270 to 310	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	60.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

