

# PTS PCA-1011

Polycarbonate + ABS

Polymer Technology and Services, LLC

Message:

PTS PCA-1011 is a Polycarbonate + ABS (PC+ABS) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

Impact Resistant

General Information			
Features	High Impact Resistance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm <sup>3</sup>	ASTM D792
Water Absorption (23°C, 24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 3.17 mm)	55.2	MPa	ASTM D638
Tensile Elongation (Break, 3.17 mm)	50	%	ASTM D638
Flexural Modulus (3.17 mm)	2210	MPa	ASTM D790
Flexural Strength (Yield, 3.17 mm)	79.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.17 mm)	590	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	110	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	104	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Shot Size	50 to 80	%	
Rear Temperature	221 to 229	°C	
Middle Temperature	224 to 235	°C	
Front Temperature	229 to 241	°C	
Nozzle Temperature	232 to 243	°C	
Processing (Melt) Temp	238 to 254	°C	
Mold Temperature	68.3 to 87.8	°C	
Injection Pressure	68.9 to 138	MPa	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

