

# Plenco 04466 (Injection)

Phenolic

Plastics Engineering Co.

## Message:

PLENCO 04466 is a heat resistant, mineral and flock filled phenolic molding compound, offering excellent mechanical strength and cosmetic properties. UL recognized under component file E40654. 04466 is available in black.

General Information			
UL YellowCard	E40654-231610		
Filler / Reinforcement	Mineral filler		
	Soft filling		
Features	Good strength		
	Heat resistance, high		
UL File Number	E40654		
Appearance	Black		
Forms	Particles		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.58	g/cm <sup>3</sup>	ASTM D792
Apparent Density	0.63	g/cm <sup>3</sup>	ASTM D1895
Molding Shrinkage - Flow	0.76	%	ASTM D955
Water Absorption (24 hr)	0.18	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale)	73		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10500	MPa	ASTM D638
Tensile Strength	49.0	MPa	ASTM D638
Tensile Elongation (Break)	0.60	%	ASTM D638
Flexural Modulus	8840	MPa	ASTM D790
Flexural Strength	83.4	MPa	ASTM D790
Compressive Strength	156	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	18.2	J/m	ASTM D256
Notched Izod Impact	17	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	162	°C	ASTM D648
Continuous Use Temperature	203	°C	ASTM D794
CLTE - Flow	4.6E-5	cm/cm/°C	ASTM E831

Thermal Conductivity (100°C)	0.54	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+11	ohms·cm	ASTM D257
Dielectric Strength <sup>1</sup>	11	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.70		ASTM D150
Dissipation Factor (1 MHz)	0.069		ASTM D150
Arc Resistance	182	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Oxygen Index	27	%	ASTM D2863

#### Additional Information

The value listed as Thermal Conductivity, ASTM C177 was tested according to the ASTM E1461 standard. The value listed as Mold Shrink, Linear-Flow, ASTM D955 was tested according to the ASTM D6289 standard. The value listed as Comparative Tracking Index, UL 746 was tested according to ASTM D3638. Post Shrinkage, ASTM D6289, 72hr, 120°C: 0.27% Drop Ball Impact, PLENCO Method: 98 J/m

Injection	Nominal Value	Unit
Suggested Shot Size	20 - 80	%
Rear Temperature	66.0 - 82.0	°C
Front Temperature	82.0 - 99.0	°C
Processing (Melt) Temp	104 - 115	°C
Mold Temperature	165 - 182	°C
Injection Pressure	6.20 - 11.0	MPa
Back Pressure	0.300	MPa
Screw Speed	< 60	rpm
Cushion	3.00	mm

#### Injection instructions

Injection Time: 3-8 sec

#### NOTE

- Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT