

# Karina STRAW PVC COMPOUND 701-38/ 14-F-IS-BZ

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

## Message:

HEAVY METAL FREE PVC COMPOUND RECOMMENDED FOR PROFILES EXTRUSION. ALSO RECOMMENDED FOR PLUG INJECTION.

General Information	
Uses	Reflectors
Appearance	Straw
Processing Method	Injection Molding
	Profile Extrusion

Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup>	1.40 to 1.46	g/cm <sup>3</sup>	IEC 60811-1-3
Color	OK		ME 12
Color a	-1.54 to 1.46		ME 12
Color b	7.52 to 10.5		ME 12
Color L	74.7 to 77.7		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	68 to 72		NBR 7456
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	> 6.37	MPa	IEC 60811-1-1
Tensile Strain (Yield)	> 250	%	IEC 60811-1-1

## NOTE

1. 24 hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT