

HiFill® PA12 GF30 L

Polyamide 12

Techmer Engineered Solutions

Message:

HiFill® PA12 GF30 L is a Polyamide 12 (Nylon 12) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America. Primary characteristic: lubricated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	108	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	5520	MPa	ASTM D790
Flexural Strength	150	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	150	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	138	°C	
1.8 MPa, Unannealed	160	°C	
CLTE - Flow	4.1E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	18	kV/mm	ASTM D149
NOTE			
1.	Method A (Short-Time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

