

HiFill® PA6 GF14 L

Polyamide 6
Techmer Engineered Solutions

Message:

HiFill® PA6 GF14 L is a Polyamide 6 (Nylon 6) product filled with 14% glass fiber. It can be processed by injection molding and is available in North America.
Characteristics include:
Flame Rated
Lubricated

General Information			
Filler / Reinforcement	Glass Fiber,14% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.60	%	ASTM D955
Water Absorption (24 hr)	1.4	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	107	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	3100	MPa	ASTM D790
Flexural Strength	13.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	213	°C	
1.8 MPa, Unannealed	196	°C	
CLTE - Flow	4.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹	20	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	82.2	°C
Drying Time	4.0	hr
Rear Temperature	260 to 304	°C
Middle Temperature	260 to 304	°C
Front Temperature	260 to 304	°C
Processing (Melt) Temp	243 to 271	°C
Mold Temperature	65.6 to 93.3	°C
Back Pressure	0.00 to 0.345	MPa
Screw Speed	30 to 60	rpm

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

