

Luran® S 796M

Acrylonitrile Styrene Acrylate
Styrolution

Message:

Luran S 796M is suitable for extrusion and injection molding. It provides a medium flowability and enhanced impact strength.

General Information			
UL YellowCard	E108538-100840265		
Features	Good Impact Resistance		
	Medium Flow		
Uses	Automotive Applications		
	Sheet		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage	0.50 to 0.90	%	ISO 294-4
Water Absorption			ISO 62
Saturation, 23°C	1.7	%	
Equilibrium, 23°C, 50% RH	0.35	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	65.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	41.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.5	%	ISO 527-2
Flexural Stress	60.0	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Tensile Elongation - MD (Break)	13	%	
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179
-30°C	5.0	kJ/m ²	
23°C	30	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	5.0	kJ/m ²	
23°C	25	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	100	°C	ISO 75-2/B
1.8 MPa, Annealed	95.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	104	°C	ISO 306/A50
--	90.0	°C	ISO 306/B50
CLTE - Flow	8.0E-5 to 1.1E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.17	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Dielectric Constant (100 Hz)	3.80		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	0.010		
1 MHz	0.025		
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	240 to 280	°C	
Mold Temperature	60.0	°C	
Injection Velocity	200	mm/sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT