

# Wanthane® WHT-1585

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

Message:

WHT-1585 is polyester-based TPU for injection molding and extrusion applications, supplied in form of transparent, translucent, colorless or slightly yellowish pellets with excellent strength , resilience and abrasion resistance

Applications:

Shoes, Seals, Cable, Compounding, Belt etc

General Information			
Features	Good Abrasion Resistance		
	Good Strength		
	Resilient		
Uses	Belts/Belt Repair		
	Compounding		
	Footwear		
	Seals		
	Wire & Cable Applications		
Appearance	Colorless		
	Translucent		
	Transparent - Slight Yellow		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	86		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	6.00	MPa	
300% Strain	11.0	MPa	
Tensile Strength	28.0	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Tear Strength	100	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-33.0	°C	ASTM D3417

Injection	Nominal Value	Unit
Drying Temperature	90.0 to 100	°C
Drying Time	2.0 to 3.0	hr
Rear Temperature	185	°C
Middle Temperature	190	°C
Front Temperature	195	°C
Nozzle Temperature	200	°C
Injection Pressure	70.0	MPa
Extrusion	Nominal Value	Unit
Drying Temperature	90.0 to 100	°C
Drying Time	3.0 to 4.0	hr
Cylinder Zone 1 Temp.	190	°C
Cylinder Zone 3 Temp.	195	°C
Cylinder Zone 5 Temp.	200	°C
Die Temperature	200	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT