

Escorene™ Ultra FL 00112

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

Message:

FL 00112 is a copolymer of ethylene and vinyl acetate with low crystal point

General Information			
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Vinyl Acetate Content	12.0	wt%	ExxonMobil Method
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	100	MPa	ASTM D882
1% secant, TD	110	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Fracture	30.0	MPa	ASTM D882
TD: Fracture	29.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	590	%	ASTM D882
TD: Fracture	620	%	ASTM D882
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	75.0	°C	ASTM D1525
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

