SILVER® ABS 323G15

Acrylonitrile Butadiene Styrene

Guangdong Silver Age Sci & Tech. Co., Ltd

Message:

SILVER® Modified ABS is applied to many fields, such as computer fittings, OA equipment and fittings, appliance crust and electronic fittings. In addition, the custom—made products should be developed by buyers 'requirements in order to meet special usage. Glass Fiber Reinforced ABS Characteristics: easy molding, high rigidity, good dimension stability, UL-94 VO/1.5 Application: trump case, fan crust, camera crust

| General Information | | | |
|--|----------------------------------|-------------------|-------------|
| Filler / Reinforcement | Glass Fiber,15% Filler by Weight | | |
| Features | Good Dimensional Stability | | |
| | Good Moldability | | |
| | High Rigidity | | |
| | | | |
| Uses | Camera Applications | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.15 | g/cm ³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (230°C/3.8 kg) | 5.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ | 70.0 | MPa | ASTM D638 |
| Tensile Elongation ² (Break) | 3.3 | % | ASTM D638 |
| Flexural Modulus ³ | 3000 | MPa | ASTM D790 |
| Flexural Strength ⁴ | 90.0 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (Area) (23°C) | 8.00 | kJ/m² | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 98.0 | °C | ASTM D648 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 200 to 230 | °C | |
| NOTE | | | |
| 1. | 50 mm/min | | |
| 2. | 50 mm/min | | |
| 3. | 5.5 mm/min | | |
| 4. | 5.5 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

