

Ateva® 2020

Ethylene Vinyl Acetate Copolymer

Celanese EVA Performance Polymers

Message:

This resin is commonly used for extrusion coating, coextrusion and specialty lamination applications.

General Information	
Features	Copolymer
Uses	Coating Applications
	Laminates
Agency Ratings	EC 1907/2006 (REACH)
Forms	Pellets
Processing Method	Coextrusion
	Extrusion Coating
	Laminating

Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Vinyl Acetate Content	20.0	wt%	

Films	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D882A
MD : Break	15.0	MPa	
TD : Break	13.0	MPa	
Tensile Elongation ²			ASTM D882A
MD : Break	520	%	
TD : Break	610	%	

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	51.0	°C	ASTM D1525
Peak Melting Temperature	83.0	°C	ASTM D3418

Extrusion	Nominal Value	Unit
Melt Temperature	< 210	°C

NOTE	
1.	500 mm/min
2.	500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT