

ALCUDIA® LDPE 2303-F

Low Density Polyethylene

REPSOL

Message:

ALCUDIA® 2303F is a low density polyethylene grade, produced by high pressure tubular technology, suitable for blown or cast film applications. This material offers easy processability and good balance of mechanical and optical properties. It does not contain any additives.

TYPICAL APPLICATIONS

General packaging film.

Heavy duty sacks.

Shrink film with high mechanical resistance.

Recommended melt temperature range from 180 to 210°C. Processing conditions should be optimised for each production line.

General Information			
Features	Optical		
	Workability, good		
	Compliance of Food Exposure		
	No additive		
Uses	Packaging		
	Films		
	Heavy packing bag		
Agency Ratings	European food contact, not rated		
Processing Method	Blow film		
	cast film		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.921	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.30	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Dynamic, Blown Film)	> 0.40		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	200	µm	
Tensile Stress			ISO 527-3
MD: Yield, 200 µm, blown film	9.00	MPa	ISO 527-3
TD: Yield, 200 µm, blown film	9.00	MPa	ISO 527-3
MD: Fracture, 200 µm, blown film	21.0	MPa	ISO 527-3
TD: Fracture, 200 µm, blown film	20.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Fracture, 200 µm, blown film	480	%	ISO 527-3
TD: Fracture, 200 µm, blown film	500	%	ISO 527-3

Dart Drop Impact (200 µm, blown film)	900	g	ISO 7765-1
Elmendorf Tear Strength			ISO 6383-2
MD: 200 µm, blown film	5.8	N	ISO 6383-2
TD: 200 µm, blown film	9.3	N	ISO 6383-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	96.0	°C	ISO 306/A
Optical	Nominal Value	Unit	Test Method
Gloss (45 °, 200 µm, blown film)	50		ASTM D2457
Haze (200 µm, blown film)	12	%	ASTM D1003
Additional Information			
Data taken from 200 µm thickness film, blow up ratio 2.25:1, frost line height 60 cm.			
Extrusion	Nominal Value	Unit	
Melt Temperature	180 - 210	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

